

PROTEQ™ C4T4

Polypropylene Copolymer

Marplex Australia Pty. Ltd.

Message:

PROTEQ™ C4T4 is a 20% Talc filled general purpose grade of polypropylene copolymer. It is used in applications where high rigidity and ductility are required.

Note: The letter U in the product name indicates that UV stabiliser has been added (PROTEQ™ C4UT4)

General Information			
Filler / Reinforcement	Talc, 20% Filler by Weight		
Features	Copolymer		
	Ductile		
	General Purpose		
	High Rigidity		
Uses	General Purpose		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	1.2	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	67		
Shore D, 15 sec	63		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.20 mm)	25.0	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	100	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	1900	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	38.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	60	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	650	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	130	°C	
1.8 MPa, Unannealed, 3.20 mm	65.0	°C	
CLTE - Flow	8.0E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Flammability Index (1.60 mm)	550	°C	AS/NZS 60695.2.12

Injection	Nominal Value	Unit
Drying Temperature	85.0 to 90.0	°C
Drying Time	2.0 to 4.0	hr
Rear Temperature	200 to 230	°C
Middle Temperature	210 to 245	°C
Front Temperature	225 to 255	°C
Processing (Melt) Temp	220 to 270	°C
Mold Temperature	50.0 to 80.0	°C
Injection Pressure	60.0 to 140	MPa
Injection Rate	Moderate	
Back Pressure	0.100 to 0.500	MPa
Screw Speed	40 to 60	rpm
Clamp Tonnage	3.0 to 6.0	kN/cm ²

NOTE

- | | |
|----|------------|
| 1. | 5.0 mm/min |
| 2. | 5.0 mm/min |
| 3. | 1.3 mm/min |
| 4. | 1.3 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

