

Tecnoprene® 3T60VB4 NERO900

Polypropylene Copolymer

SO.F.TER. SPA

Message:

Glass fiber reinforced polypropylene copolymer, blow moulding grade

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Copolymer		
Uses	Automotive Applications		
	Blow Molding Applications		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.02	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Molding Shrinkage	0.40	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	3300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	180	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	131	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (3.20 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT