

Petro Rabigh PP AZ564G

Polypropylene Impact Copolymer
Rabigh Refining & Petrochemical Co.

Message:

AZ564G is a block copolymer polypropylene intended for industrial application & thin wall applications. It has a high melt flow and formulated with nucleating agent. Injection molding parts made from this resin exhibit good impact, high stiffness and good heat stability.

Applications

Crates

Thin wall application

Industrial application

Electrical appliances

General Information			
Additive	Nucleating Agent		
Features	Block Copolymer		
	Good Impact Resistance		
	Good Stiffness		
	Heat Stabilized		
	High Flow		
	Nucleated		
Uses	Appliances		
	Crates		
	Industrial Applications		
	Thin-walled Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	39	g/10 min	ASTM D1238
Molding Shrinkage			Internal Method
Flow	1.4	%	
Across Flow	1.6	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	86		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	24.0	MPa	
Break	16.0	MPa	
Flexural Modulus	1280	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact Strength			ASTM D256
-20°C	5.0	kJ/m ²	
23°C	9.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	118	°C	ASTM D648
Vicat Softening Temperature	149	°C	ASTM D1525 ¹
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	190 to 230	°C	
NOTE			
1.	Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

