

Reny® 4501

Polyarylamide

Mitsubishi Engineering-Plastics Corp

Message:

Reny® 4501 is a Polyarylamide (PARA) material filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding. Important attributes of Reny® 4501 are:

Flame Rated

Flame Retardant

Conductive

General Information				
UL YellowCard		E41179-231772		
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Additive		Flame Retardant		
Features		Electrically Conductive		
		Flame Retardant		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.66	--	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (275°C/2.10 kg)	10	--	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (275°C/2.10 kg)	7.50	--	cm ³ /10min	ISO 1133
Molding Shrinkage	0.30	--	%	
Water Absorption				ISO 62
Saturation, 23°C	0.060	--	%	
Equilibrium, 23°C, 50% RH	0.80	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	20400	16200	MPa	ISO 527-2
Tensile Stress (Break)	107	113	MPa	ISO 527-2
Tensile Strain (Break)	0.70	0.90	%	ISO 527-2
Flexural Modulus	19100	15500	MPa	ISO 178
Flexural Stress	190	184	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.5	6.6	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	14	15	kJ/m ²	ISO 179
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				

0.45 MPa, Unannealed	236	232	°C	ISO 75-2/B
1.8 MPa, Unannealed	225	216	°C	ISO 75-2/A
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.60 mm)	V-0	--		UL 94
Injection	Dry	Unit		
Drying Temperature				
A	120		°C	
B	80.0		°C	
Drying Time				
A	> 3.0		hr	
B	> 12		hr	
Rear Temperature	260		°C	
Middle Temperature	265		°C	
Front Temperature	270		°C	
Nozzle Temperature	270		°C	
Mold Temperature	120 to 140		°C	
Injection Pressure	20.0 to 150		MPa	
Injection Rate	Moderate-Fast			
Screw Speed	60 to 150		rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

