

CP PRYME® Nylon 66 NN333HSL BK-P

Polyamide 66

Chase Plastics Services Inc.

Message:

33% glass fiber reinforced, Reprocessed Nylon 6/6, with Heat Stabilizer and Lubricant, Black

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Additive	Heat Stabilizer Lubricant		
Features	Heat Stabilized Lubricated		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.020	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	128	MPa	ASTM D638
Flexural Modulus (23°C)	6960	MPa	ASTM D790
Flexural Strength	241	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	252	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

