Huafon JF-W-3240

Polyurethane

Huafon Group Co., Ltd.

Message:

General Type

Characteristics

Hard type, good solubility with pigments, high film thickness, excellent film and thickness, good film property.

Applications

Shoes, Bags

General Information			
Features	High Hardness		
Uses	Bags		
	Footwear		
Additional Information	Nominal Value	Unit	
Solvents	DMF		
Uncured Properties	Nominal Value	Unit	
Solids Content	29 to 31	%	
Viscosity (25°C)	160 to 260	Pa·s	
Cured Properties	Nominal Value	Unit	
Tensile Modulus (100% Secant)	22.0 to 26.0	MPa	
Tensile Strength	> 40.0	MPa	
Tensile Elongation at Break	> 150	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

