

Polaris™ MR 86210

Thermoset Polyester

Ashland Performance Materials

Message:

Cast polymers - Marble Resins

Properties

High fill capability for low cost parts

General Information		
Processing Method	Casting	
Physical	Nominal Value	Unit
Solution Viscosity	250	mPa·s
Additional Information	Nominal Value	Unit
Gel to Peak	5.0	min
Peak Exotherm	154	°C
Uncured Properties	Nominal Value	Unit
Gel Time	6.0 to 16	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

