

RTP 699 X 123035 B Z

Acrylonitrile Butadiene Styrene

RTP Company

Message:

ESD Protection - Permanently Static Dissipative - FDA Compliant Ingredients - Preliminary

General Information			
Features	Electrostatic discharge protection		
	Static conduction		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	ASTM D955
Moisture Content	0.10	%	
Static Decay		sec	FTMS 101C 4046.1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1590	MPa	ASTM D638
Tensile Strength	31.0	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	1720	MPa	ASTM D790
Flexural Strength	55.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	190	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	No Break		ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8 - 9.9E+9	ohms	ASTM D257
Volume Resistivity	1.0E+7 - 9.9E+8	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	82	°C	
Drying Time	2.0	hr	
Dew Point	-18	°C	
Processing (Melt) Temp	199 - 238	°C	
Mold Temperature	49 - 93	°C	
Injection Pressure	68.9 - 103	MPa	
Injection instructions			

Do not exceed 520 °F (270 °C) melt temperature.Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

