

ACCUTECH™ POL051G40L

Polycarbonate
ACLO Compounders Inc.

Message:

ACCUTECH™POL051G40L is a polycarbonate (PC) product that contains a 40% glass fiber reinforced material. It is available in North America.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5800	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	142	MPa	ASTM D638
Fracture	141	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	4.0	%	ASTM D638
Fracture	5.0	%	ASTM D638
Flexural Modulus	11000	MPa	ASTM D790
Flexural Strength	216	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	180	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	144	°C	ASTM D648
1.8 MPa, not annealed	140	°C	ASTM D648
Additional Information			

Ash Content, ASTM D2584: 40%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

