

RheTech Polypropylene FRG130-01

Polypropylene

RheTech, Inc.

Message:

30% Glass Fiber Reinforced, Chemically Coupled, Flame Retardant, Polypropylene, Black, UL 94V-0 Compliant.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Chemical coupling		
	Flame retardancy		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	76		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	72.4	MPa	ASTM D638
Flexural Modulus	6890	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	80	J/m	ASTM D256
Dart Drop Impact	0.339	J	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	159	°C	ASTM D648
1.8 MPa, not annealed	142	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	51.7 - 65.6	°C	
Drying Time	1.0 - 2.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	191 - 199	°C	
Middle Temperature	199 - 210	°C	
Front Temperature	199 - 210	°C	
Nozzle Temperature	204	°C	
Mold Temperature	23.9 - 35.0	°C	

Injection Pressure	2.76 - 8.27	MPa
Injection Rate	Slow	
Holding Pressure	2.07 - 6.89	MPa
Back Pressure	0.345 - 0.689	MPa
Screw Speed	50 - 100	rpm

Injection instructions

Injection Speed: Slow, 0.5 to 1.0 in/minScrew RPM: Slow to Moderate, 50 to 100 RPM; Note: Purge the machine with polypropylene or polyethylene prior to shut down or change over.Cycle Time: Variable; Note: Do not leave material in the barrel for extended periods of down time. The flame retardant is temperature sensitive and will degrade when exposed to elevated temperatures for extended periods. Noxious gasses may be evolved.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

