

Grilamid® L 20 HL black 9563

Polyamide 12

EMS-GRIVORY

Message:

Grilamid® L 20 HL black 9563 is a Polyamide 12 (Nylon 12) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion.

Important attributes of Grilamid® L 20 HL black 9563 are:

- Flame Rated
- RoHS Compliant
- Good UV Resistance
- Heat Stabilizer
- Medium Viscosity

Typical applications include:

- Automotive
- Consumer Goods
- Electrical/Electronic Applications
- Engineering/Industrial Parts
- Hose/Tubing

General Information	
Additive	Heat Stabilizer UV Stabilizer
Features	Good UV Resistance Heat Stabilized Medium Viscosity
Uses	Automotive Applications Consumer Applications Electrical/Electronic Applications Engineering Parts Hydraulic Applications Industrial Applications Pneumatic Applications Power/Other Tools Tubing Wire & Cable Applications
RoHS Compliance	RoHS Compliant
Appearance	Black
Forms	Granules
Processing Method	Extrusion
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1) Secant Modulus vs. Strain (ISO 11403-1)

Shear Modulus vs. Temperature (ISO 11403-1)

Specific Volume vs Temperature (ISO 11403-2)

Physical	Dry	Conditioned	Unit	Test Method
Density	1.01	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.80	--	%	
Flow	0.80	--	%	
Water Absorption				ISO 62
Saturation, 23°C	1.5	--	%	
Equilibrium, 23°C, 50% RH	0.70	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	--	70		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1400	1100	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Yield	45.0	40.0	MPa	
Break	50.0	50.0	MPa	
Tensile Strain (Yield)	5.0	12	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	--	6.0	kJ/m ²	
23°C	--	7.0	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	115	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	45.0	--	°C	ISO 75-2/A
Continuous Use Temperature				Internal Method
-- ¹	90.0 to 110	--	°C	
-- ²	150	--	°C	
Melting Temperature ³	178	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.2E-4	--	cm/cm/°C	

Transverse	1.4E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+12	ohms	IEC 60093
Volume Resistivity	--	1.0E+13	ohms·cm	IEC 60093
Electric Strength	--	32	kV/mm	IEC 60243-1
Comparative Tracking Index	--	550	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA12, EHL, 18-010	--		ISO 1874
NOTE				
1.	Long Term			
2.	Short Term			
3.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

