

# CERTENE™ PHM-70

Polypropylene Homopolymer  
Muehlstein

Message:

PHM-70 is a certified prime grade developed for INJECTION MOLDING and COMPOUNDING general purpose applications. PHM-70 offers excellent high melt flow and easy processability. PHM-70 applications include thin-walled multi-cavity caps, closures and lids, household articles, medical syringes, and items requiring good dimensional stability free of warpage, such as straight-sided video cassette boxes. PHM-70 processing temperature is 220° to 240°C with mold at 20°- 50°C.. PHM-70 complies with FDA regulation 21CFR 177.1520 (c)1.1a concerning the Polypropylene use in contact with food articles.

General Information			
Features	Food Contact Acceptable		
	Good Dimensional Stability		
	Good Processability		
	High Flow		
	Warp Resistant		
Uses	Caps		
	Closures		
	Containers		
	Household Goods		
	Lids		
	Medical/Healthcare Applications		
	Thin-walled Parts		
Agency Ratings	FDA 21 CFR 177.1520(c) 1.1a		
Forms	Pellets		
Processing Method	Compounding		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.904	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	70	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness <sup>1</sup> (R-Scale)	104		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	36.5	MPa	ASTM D638
Tensile Elongation (Yield)	8.5	%	ASTM D638
Flexural Modulus - 1% Secant <sup>2</sup>	1450	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>3</sup> (23°C)	16	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load <sup>4</sup> (0.45 MPa, Unannealed)	98.0	°C	ASTM D648
Vicat Softening Temperature <sup>5</sup>	150	°C	ASTM D1525

Injection	Nominal Value	Unit
Processing (Melt) Temp	220 to 240	°C
Mold Temperature	20.0 to 50.0	°C

#### NOTE

1.	Test made on injection molded Type 1 tension test specimen according to ASTM D 2146.
2.	1.3 mm/min
3.	Test made on injection molded Type 1 tension test specimen according to ASTM D 2146.
4.	Test made on injection molded Type 1 tension test specimen according to ASTM D 2146.
5.	Test made on injection molded Type 1 tension test specimen according to ASTM D 2146.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

