Caltex PP MT43

Polypropylene

GS Caltex

Message:

Caltex PP MT43 is a Polypropylene material filled with mineral. It is available in Asia Pacific.

Important attributes of Caltex PP MT43 are:

Flame Rated

Heat Resistant

High Stiffness

Typical applications include:

Appliances

Automotive

Electrical/Electronic Applications

General Information			
UL YellowCard	E119841-220403		
Filler / Reinforcement	Mineral		
Features	High Heat Resistance		
	High Stiffness		
Uses	Appliances		
	Automotive Applications		
	Electrical Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR)	9.0	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.1	%	
Across Flow	1.0	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	93		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.4	МРа	ASTM D638
Tensile Elongation (Break)	40	%	ASTM D638
Flexural Modulus	2940	МРа	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45	407	05	ACTA A T C 10
MPa, Unannealed)	137	°C	ASTM D648
Vicat Softening Temperature	153	°C	ASTM D1525

Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	210 to 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

