

REPOL® H250FG

Polypropylene Homopolymer

Reliance Industries Limited

Message:

REPOL Polypropylene H250FG is manufactured using Unipol PP process which combines the production efficiency of gas phase fluidized bed reactor technology with the high activity stereospecific catalyst system. Repol H250FG is recommended for use in Fiber Spinning operations, for making multifilament yarn and staple fibre.

General Information			
Features	Good Color Stability		
	Good Processability		
	Homopolymer		
Uses	BCF Yarn		
	Staple Fibers		
Forms	Pellets		
Processing Method	Fiber (Spinning) Extrusion		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	25	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	34.0	MPa	ASTM D638
Tensile Elongation ² (Yield)	11	%	ASTM D638
Flexural Modulus - 1% Secant ³	1650	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	25	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	104	°C	ASTM D648
NOTE			
1.	Type I, 50 mm/min		
2.	Type I, 50 mm/min		
3.	Type I		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

