

OXPEKK® IG200

Polyetherketoneketone

Oxford Performance Materials, Inc.

Message:

OXPEKK® IG200 is a Polyetherketoneketone (PEKK) material. It is available in Europe or North America for injection molding. Primary attribute of OXPEKK® IG200: Crystalline.

Typical application of OXPEKK® IG200: Medical/Healthcare

General Information			
Features	Crystalline		
Uses	Body Implants		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/8.4 kg)	100 to 120	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4	%	ASTM D955
Water Absorption (24 hr)	< 0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	88		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4410	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	138	MPa	
Break	110	MPa	
Tensile Elongation			ASTM D638
Yield	4.0	%	
Break	12	%	
Flexural Modulus	4550	MPa	ASTM D790
Flexural Strength (5.0% Strain)	193	MPa	ASTM D790
Compressive Strength	207	MPa	ASTM D695
Shear Strength	138	MPa	ASTM D732
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	175	°C	ASTM D648
Glass Transition Temperature	163	°C	DSC
Melting Temperature	360	°C	DSC
CLTE - Flow	2.1E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

