

RTP 2099 X 121249 B

Poly(lactic Acid

RTP Company

Message:

Standard Nucleator - Glass Fiber - 78% Renewable Resource Content

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	Nucleating agent		
Features	Nucleated		
	Updatable resources		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Moisture Content	0.020	%	
Primary Additive	20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8270	MPa	ASTM D638
Tensile Strength	96.5	MPa	ASTM D638
Tensile Elongation (Yield)	1.5	%	ASTM D638
Flexural Modulus	8620	MPa	ASTM D790
Flexural Strength	117	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	48	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	320	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	152	°C	ASTM D648
1.8 MPa, not annealed	148	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	54.4	°C	
Drying Time	2.0 - 6.0	hr	
Dew Point	-40.0	°C	
Processing (Melt) Temp	171 - 193	°C	
Mold Temperature	82.2 - 104	°C	
Injection Pressure	55.2 - 103	MPa	
Injection instructions			
Desiccant Type Dryer Required.			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

