

VALOX™ HX3061HP resin

Polybutylene Terephthalate

SABIC Innovative Plastics

Message:

PBT for compounding/fibers only. Not intended for injection molding. Biocompatible. Melt viscosity: 250C at 21.6 kgf is 1450-1850 poise. Available in Natural color (1001) only.

General Information			
Features	Biocompatibility		
Uses	Composite		
	Fiber		
Appearance	Natural color		
Processing Method	Compound extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	50	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	45.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	1.5 - 2.0	%	Internal method
Transverse flow: 3.20mm	1.5 - 2.0	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.34	%	ISO 62
Equilibrium, 23°C, 50% RH	0.080	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2600	MPa	ASTM D638
--	2600	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	58.0	MPa	ASTM D638
Yield	50.0	MPa	ISO 527-2/50
Fracture ³	26.0	MPa	ASTM D638
Fracture	49.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	3.7	%	ASTM D638
Yield	3.2	%	ISO 527-2/50
Fracture ⁵	140	%	ASTM D638
Fracture	8.6	%	ISO 527-2/50
Flexural Modulus			

50.0mm span ⁶	2400	MPa	ASTM D790
-- ⁷	2200	MPa	ISO 178
Flexural Stress			
--	80.0	MPa	ISO 178
Yield, 50.0mm span ⁸	83.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	4.8	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	35	J/m	ASTM D256
23°C	37	J/m	ASTM D256
-30°C ¹⁰	3.4	kJ/m ²	ISO 180/1A
23°C ¹¹	4.4	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	25.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	120	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	49.0	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	49.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	167	°C	ASTM D1525 ¹³
--	173	°C	ISO 306/B50
--	169	°C	ISO 306/B120
Linear thermal expansion coefficient			
Flow: -40 to 40°C	7.6E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	7.8E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity	165	Pa · s	Internal method
Extrusion	Nominal Value	Unit	
Drying Temperature	110 - 120	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	200 - 230	°C	
Cylinder Zone 2 Temp.	240 - 255	°C	
Cylinder Zone 3 Temp.	240 - 275	°C	
Cylinder Zone 4 Temp.	240 - 275	°C	
Adapter Temperature	240 - 275	°C	
Melt Temperature	245 - 260	°C	
Die Temperature	240 - 275	°C	
Extrusion instructions			
Drying Time (Cumulative): 8 hrsWater Bath Temperature: 25 - 35 °C			
NOTE			

1.	5.0 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

