

Mytex® AS66K-01

Compounded Polypropylene

Mytex Polymers

Message:

Talc filled compounded polypropylene produced for automotive interior applications using Mytex® Technology.

General Information			
Filler / Reinforcement	Talc		
Uses	Automotive Applications		
	Automotive Interior Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.980	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	50		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	19.0	MPa	ASTM D638
Flexural Modulus - Tangent ²	1300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	650	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	90.0	°C	ASTM D648
NOTE			
1.	50 mm/min		
2.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT