

SWANCOR Epoxy 901-2T

Epoxy; Epoxide
SWANCOR IND. CO., LTD.

Message:

Suitable for CIPP application
Excellent mechanical properties and chemical resistance as SWANCOR 901.
High Thix Index >3.5.
Medium elongation

General Information			
Features	Acid Resistant		
	Aliphatic		
	Good Chemical Resistance		
	Salt Water/Spray Resistant		
Forms	Liquid		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	100	°C	ASTM D648
Thermoset	Nominal Value	Unit	Test Method
Shelf Life (25°C)	17	wk	
Thermoset Mix Viscosity (25°C)	3000	cP	ASTM D2393

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT