

Kepital® F10-01

Acetal (POM) Copolymer
Korea Engineering Plastics Co., Ltd

Message:

A high viscosity grade for extrusion of round bars, sheets and tubes. It is also suitable for injection molding of thick-walled, void-free and sink mark reduced parts.

General Information	
UL YellowCard	E120354-220440
Uses	Piping
	Sheet
	Tubing
RoHS Compliance	RoHS Compliant
Forms	Pellets
Processing Method	Extrusion
	Pipe Extrusion

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	3.0	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.00 mm)	2.2	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	63.0	MPa	ISO 527-2
Nominal Tensile Strain at Break (23°C)	40	%	ISO 527-2
Flexural Modulus (23°C)	2350	MPa	ISO 178
Flexural Stress (23°C)	82.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	7.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	96.0	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Dielectric Strength	19	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT