

Novablend™ 9562

Polyvinyl Chloride Alloy

PolyOne Corporation

Message:

Custom Molding

General Information			
Features	General Purpose		
	High Impact Resistance		
	Medium Flow		
Uses	Construction Applications		
	General Purpose		
	Outdoor Applications		
Appearance	Opaque		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.20	g/cm ³	ASTM D792
Spiral Flow	58.4	cm	
Molding Shrinkage - Flow	0.20 to 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	79		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	2240	MPa	ASTM D638
Tensile Strength ³ (Yield)	46.2	MPa	ASTM D638
Tensile Elongation ⁴ (Break)	50	%	ASTM D638
Flexural Modulus	2280	MPa	ASTM D790
Flexural Strength	68.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256A
-18°C, 3.18 mm, Injection Molded	130	J/m	
0°C, 3.18 mm, Injection Molded	640	J/m	
23°C, 3.18 mm, Injection Molded	960	J/m	
Drop Impact Resistance (23°C, 3.18 mm)	89.0	J/cm	ASTM D4226
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.18 mm, Injection Molded	77.3	°C	
0.45 MPa, Annealed, 3.18 mm ⁵	82.0	°C	

1.8 MPa, Unannealed, 3.18 mm, Injection Molded	64.4	°C	
1.8 MPa, Annealed, 3.18 mm ⁶	74.1	°C	
CLTE - Flow	1.4E-4	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Processing (Melt) Temp	199 to 210	°C	

NOTE

1.	Properties reported for Natural color.
2.	Type I, 51 mm/min
3.	Type I, 51 mm/min
4.	Type I, 51 mm/min
5.	Injection Molded
6.	Injection Molded

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

