

Auracell® MSS

Cellulose Acetate
Rotuba Extruders, Inc.

Message:

Auracell® MSS is a Cellulose Acetate (CA) product. It can be processed by injection molding and is available in Europe or North America. Primary characteristic: eco-friendly/green.

General Information			
Features	Renewable Resource Content		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Water Absorption (23°C, 24 hr)	2.5	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	31		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	18.6	MPa	
Break, 23°C	27.2	MPa	
Break, 70°C	9.31	MPa	
Tensile Elongation (Break)	53	%	ASTM D638
Flexural Modulus	793	MPa	ASTM D790
Flexural Strength (Yield)	26.5	MPa	ASTM D790
Deformation Under Load			ASTM D621
50°C, 6.9 MPa	8.00	%	
50°C, 14 MPa	36.0	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	69	J/m	
23°C	350	J/m	
Aging	Nominal Value	Unit	Test Method
Accelerated Aging - wt. lost, 72 hr (82°C)	5.4	wt%	ASTM D706
Flow Beginning Temperature	138	°C	ASTM D569
Soluble Matter Loss	0.80	%	ASTM D570
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	2.0	hr	
Dew Point	-40.0 to -28.9	°C	
Rear Temperature	177 to 188	°C	

Middle Temperature	177 to 188	°C
Front Temperature	177 to 188	°C
Nozzle Temperature	188 to 199	°C
Mold Temperature	37.8 to 82.2	°C
Injection Pressure	6.55 to 7.58	MPa
Back Pressure	0.00 to 0.345	MPa
Vent Depth	0.051 to 0.076	mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

