

Nanjing Hongrui PA66 A1304

Polyamide 66

Nanjing Hongrui Engineering Plastics Co., Ltd.

Message:

Nanjing Hongrui PA66 A1304 is a Polyamide 66 (Nylon 66) material filled with 20% glass fiber. It is available in Asia Pacific.

Important attributes of Nanjing Hongrui PA66 A1304 are:

Flame Rated

Flame Retardant

Typical application of Nanjing Hongrui PA66 A1304: Electrical/Electronic Applications

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Uses	Connectors		
	Electrical/Electronic Applications		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	80.0	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	5000	MPa	ASTM D790
Flexural Strength	160	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	6.00	kJ/m²	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	210	°C	ASTM D648
Melting Temperature	255	°C	

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149

Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

