

POLYfill PP CQX10030E10

Polypropylene

Polykemi AB

Message:

Mineral reinforced Elastomer modified

General Information			
Filler / Reinforcement	Mineral,30% Filler by Weight		
Additive	Impact Modifier		
Features	Impact Modified		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.2 to 1.4	%	
Flow	1.2 to 1.4	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	19.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	7.0	%	
Break	23	%	
Flexural Modulus (23°C)	1700	MPa	ISO 178
Flexural Stress	35.0	MPa	ISO 178
Scratch Resistance - 10 N Fine Structure ¹	< 0.100	dL	ISO 1518/D65
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	4.0	kJ/m ²	
23°C	10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-20°C	45	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ²			
0.45 MPa, Unannealed	111	°C	ISO 75-2/B
1.8 MPa, Unannealed	58.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	144	°C	ISO 306/A50
--	70.0	°C	ISO 306/B50
CLTE - Flow	7.0E-5 to 9.0E-5	cm/cm/°C	Internal Method

Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature (2.00 mm)	750	°C	IEC 60695-2-13
NOTE			
1.	Test performed on black plaques with fine (Standex MT9078) and rough (Standex MT11435) structure		
2.	120°C/hr		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

