

COPEC® CC7FDN (Series: VS/CR/AD1)

Thermoplastic Elastomer

KRAIBURG TPE

Message:

The VS/CR/AD1 Series is your material solution for applications in the consumer electronics section. The series features an exceptionally silky and velvety surface, accompanied by an outstanding resistance to skin oil, sun cream and olive oil. The compounds convince due to their excellent adhesion to polar thermoplastics such as ABS, PC and PC/ABS.

Typical applications

Ear phones

Game consoles

Handles and grips for consumer applications

Remote controls

Seals

Material advantages

Easy coloring (compounds in natural colors)

Excellent color stability

Good weathering resistance

Insert molding possible

Pleasant surface feel (Soft touch)

Resistance against skin oil, sunscreens and olive oil

Smooth and silky surface

UL 94 HB listed

General Information			
UL YellowCard	E214822-101834812	E353857-101835063	
Features	Good coloring		
	Good adhesion		
	Good weather resistance		
	Oil resistance		
	Excellent appearance		
Uses	Handle		
	Electrical/Electronic Applications		
	Seals		
	Soft handle		
Appearance	Natural color		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	73		ISO 7619
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Break)	9.50	MPa	ISO 37
Tensile Elongation ² (Break)	850	%	ISO 37
Tear Strength ³	28	kN/m	ISO 34-1

Additional Information	Nominal Value	Unit	Test Method
Adhesion to ABS	34.0	kN/m	Renault D41/1916
Adhesion to PC	31.0	kN/m	Renault D41/1916
Extrusion	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Cylinder Zone 1 Temp.	160	°C	
Cylinder Zone 2 Temp.	180	°C	
Cylinder Zone 3 Temp.	200	°C	
Die Temperature	220	°C	
NOTE			
1.	Type S2, 200 mm/min		
2.	Type S2, 200 mm/min		
3.	Method B, right-angle specimen (cut)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT