

Styrolution PS 7120

High Impact Polystyrene
INEOS Styrolution Group GmbH

Message:

Styrolution PS 7120 is a High Impact Polystyrene product. It can be processed by injection molding and is available in Latin America or North America. Applications of Styrolution PS 7120 include bags/liners and food contact applications. Characteristics include:
Flame Rated
Impact Resistant
High ESCR (Stress Crack Resistant)
High Stiffness

General Information			
Features	High ESCR (Stress Crack Resist.)		
	High Impact Resistance		
	High Stiffness		
	Low Temperature Impact Resistance		
Uses	Liners		
	Non-specific Food Applications		
UL File Number	E57787		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Apparent Density ¹	0.59 to 0.64	g/cm ³	
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	2.3	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	42		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1790	MPa	ASTM D638
Tensile Strength (Yield, 23°C)	20.3	MPa	ASTM D638
Tensile Elongation (Break)	55	%	ASTM D638
Flexural Modulus	1760	MPa	ASTM D790
Flexural Strength	44.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	87.2	°C	

Vicat Softening Temperature	103	°C	ASTM D1525 ²
CLTE - Flow	9.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (3.18 mm)	16	kV/mm	ASTM D149
Dielectric Constant (1.00 mm, 1 MHz)	2.50		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value		Test Method
Gardner Gloss (60°)	10		ASTM D523
Injection	Nominal Value	Unit	
Processing (Melt) Temp	182 to 277	°C	
Mold Temperature	37.8 to 82.2	°C	
NOTE			
1.	without external lubricant		
2.	Rate B (120°C/h), Loading 1 (10 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

