

Kepital® F30-03

Acetal (POM) Copolymer

Korea Engineering Plastics Co., Ltd

Message:

Low viscosity,high flow grade for injection molding with thin walled parts.

General Information			
Features	Copolymer		
	Good liquidity		
	Thermal stability, good		
Uses	Thin wall parts		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	28	g/10 min	ISO 1133
Molding Shrinkage - Flow (3.00 mm)	2.0	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break, 23°C)	65.0	MPa	ISO 527-2
Nominal Tensile Strain at Break (23°C)	25	%	ISO 527-2
Flexural Modulus (23°C)	2700	MPa	ISO 178
Flexural Stress (23°C)	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	5.5	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	101	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Dielectric Strength	19	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

