

# HANWHA KH-10

Polyvinyl Chloride

Hanwha Chemical

## Message:

Feature: Low viscosity, low deterioration and low absorption. High insulating resistance and high transparency.

Use: General use, slush forming, rotational forming erasers, DIP forming, flooring/wall paper/leather top coatings

| General Information                      |                     |                   |                 |
|--|---------------------|-------------------|-----------------|
| Features                                 | Low viscosity       |                   |                 |
| Uses                                     | General             |                   |                 |
|  | Coating application |                   |                 |
|  | Paper coating       |                   |                 |
| Appearance                               | Clear/transparent   |                   |                 |
| Physical                                 | Nominal Value       | Unit              | Test Method     |
| Apparent Density                         | 0.19 - 0.27         | g/cm <sup>3</sup> | ASTM D1895      |
| Volatile Matter                          |                     | %                 | ASTM D3030      |
| Particle size-100Mesh(150μm) Sieve Pass% | 100                 | %                 | Internal method |
| Brokfield viscosity-cps/6rpm             |                     |                   | ASTM D1824      |
| degree of polymerization                 |                     |                   |                 |
| DP                                       | 1600 - 1800         |                   | JIS K6720-2     |
| K-Value                                  | 76.0                |                   | DIN 53726       |
| Additional Information                   | Nominal Value       | Test Method       |                 |

Liquidity: Dilatant

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

