

Diamond ABS 7500E

Acrylonitrile Butadiene Styrene
Network Polymers, Inc.

Message:

Diamond ABS 7500E is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by extrusion and is available in North America. Characteristics include:
Flame Rated
REACH Compliant
RoHS Compliant
WEEE Compliant
Impact Resistant

General Information			
UL YellowCard	E51193-101898799		
Features	Ultra High Impact Resistance		
Agency Ratings	EC 1907/2006 (REACH)		
	EU 2002/96/EC (WEEE)		
RoHS Compliance	RoHS Compliant		
UL File Number	E150937		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹			ASTM D1238
200°C/5.0 kg	0.50	g/10 min	
230°C/3.8 kg	1.7	g/10 min	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	46.2	MPa	ASTM D638
Flexural Modulus - Tangent ³	2170	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	400	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 3.18 mm	80.0	°C	
1.8 MPa, Annealed, 3.18 mm	96.1	°C	
Vicat Softening Temperature	107	°C	ASTM D1525 ⁴
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	80.0 to 85.0	°C
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	190 to 250	°C
Middle Temperature	190 to 250	°C
Front Temperature	190 to 250	°C
Mold Temperature	40.0 to 80.0	°C
Injection Rate	Moderate-Fast	

NOTE

- | | |
|----|------------------|
| 1. | Procedure A |
| 2. | 51 mm/min |
| 3. | 1.3 mm/min |
| 4. | Loading 1 (10 N) |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT