

PermaStat® 601

Acrylonitrile Butadiene Styrene

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
PermaStat® 600 materials are ABS with a permanent anti-static additive. The products are non-migrating, independent of humidity and colorable. The products meet static decay requirements of MIL B-80705C.

General Information			
Additive	Antistatic property (10)		
Features	Antistatic property		
Uses	Conveyor		
	Calculator		
	Printing press		
	Printing machine parts		
Agency Ratings	MIL B-81705C		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30 - 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2960	MPa	ASTM D638
Tensile Strength (Yield)	41.0	MPa	ASTM D638
Tensile Elongation (Break)	5.5	%	ASTM D638
Flexural Modulus	2830	MPa	ASTM D790
Flexural Strength (Yield)	69.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	240	J/m	ASTM D4812
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+10	ohms	ASTM D257
Volume Resistivity	1.0E+9	ohms · cm	ASTM D257

Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm, Values per RTP Company testing.)	HB		UL 94
Additional Information			
Molding Shrinkage, ASTM D 955, 3.175mm: 3-5mm/mTensile Elongation, ASTM D 638: 4-7%Static Decay, FTMS-4046.1, Mil B-81705C: <2.0 secondsVolume Resistivity, ASTM D 257: 10000000000 - 100000000000 ohm-cmSurface Resistivity, ASTM D 257: 100000000000 - 1000000000000 ohm/sq			
Injection	Nominal Value	Unit	
Rear Temperature	216 - 288	°C	
Middle Temperature	216 - 288	°C	
Front Temperature	216 - 288	°C	
Mold Temperature	66.0 - 93.0	°C	
Injection Pressure	68.9 - 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

