

# Sumiliteresin® PR-51587 I

Phenolic

SBHPP

## Message:

SUMILITERESIN® PR-51587 I is a Tall oil modified novolac type phenolic resin. It is generally applied for tire and rubber as reinforcement.

### Characteristics

SUMILITERESIN® PR-51587 I is a Tall oil modified phenolic resin with flake shape. It contains modification of tall oil modified to improve flexibility properties and good compatibility mixture to rubber with low money viscosity.

General Information		
Uses	Tires	
Appearance	Brown	
Forms	flake	
Physical	Nominal Value	Unit
Flow Length (125°C)	5.00 - 9.00	cm
Softening Point - B&R;	85 - 92	°C
Free Phenol - GC		%
Thermal	Nominal Value	Unit
Melting Temperature	62.0 - 72.0	°C
Uncured Properties	Nominal Value	Unit
Gel Time (165°C)	0.33 - 0.75	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

