

# Wanthane® WHT-7190

Polycarbonate + TPU

Wanhua Chemical Group Co., Ltd.

Message:

WHT-7190 is polycarbonate-based TPU, supplied in form of transparent, translucent, colorless or slightly yellowish pellets with the characteristics such as:  
Higher Mechanical Strength  
As good hydrolytic stability as polyether-based TPU  
Better chemical resistance than other polyester-based TPUs  
Better weather resistance such as heat and fungus resistance than common polyester-based TPUs  
WHT-7180 is polycarbonate-based TPU, supplied in form of transparent, translucent, colorless or slightly yellowish pellets with the characteristics such as:  
Higher Mechanical Strength  
As good hydrolytic stability as polyether-based TPU  
Better chemical resistance than other polyester-based TPUs  
Better weather resistance such as heat and fungus resistance than common polyester-based TPUs  
Applications:  
Wire & Cable, Film & Sheet, Hose & Tube, Animal Tag, Fire Hose, Sports Equipments etc.

General Information			
Features	Fungus Resistant		
	Good Chemical Resistance		
	Good Strength		
	Hydrolytically Stable		
	Medium Heat Resistance		
Uses	Film		
	Hose		
	Sheet		
	Sporting Goods		
	Tubing		
	Wire & Cable Applications		
Appearance	Colorless		
	Translucent		
	Transparent - Slight Yellow		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.24	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	90		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method

Tensile Stress			ASTM D412
100% Strain	10.0	MPa	
300% Strain	35.0	MPa	
Tensile Strength	40.0	MPa	ASTM D412
Tensile Elongation (Break)	330	%	ASTM D412
Tear Strength	110	kN/m	ASTM D624
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	195	°C	
Middle Temperature	200	°C	
Front Temperature	205	°C	
Nozzle Temperature	200	°C	
Injection Pressure	85.0	MPa	
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0 to 90.0	°C	
Drying Time	3.0 to 4.0	hr	
Cylinder Zone 1 Temp.	190	°C	
Cylinder Zone 3 Temp.	195	°C	
Cylinder Zone 5 Temp.	200	°C	
Die Temperature	195	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

