

Kepamid® 2325GVS

Polyamide 66

Korea Engineering Plastics Co., Ltd

Message:

KEPAMID 2325GVS is a 25% glass fiber reinforced and flame retardant polyamide-66.

UL94 V-0 flame resistance with good mechanical and thermal properties.

It is applicable to automotive, electrical, electronic, and industrial parts.

General Information			
UL YellowCard	E120354-256744		
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Features	Flame Retardant		
Uses	Automotive Applications		
	Electrical Parts		
	Electrical/Electronic Applications		
	Industrial Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.54	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (275°C/2.16 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	0.30 to 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	137	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	8340	MPa	ASTM D790
Flexural Strength (23°C)	206	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	255	°C	
1.8 MPa, Unannealed	235	°C	
Melting Temperature	260	°C	DSC
Flammability	Nominal Value		Test Method
Flame Rating (0.800 mm)	V-0		UL 94
Injection	Nominal Value	Unit	
Hopper Temperature	260 to 300	°C	

Rear Temperature	260 to 300	°C
Middle Temperature	260 to 300	°C
Front Temperature	260 to 300	°C
Nozzle Temperature	260 to 300	°C
Mold Temperature	40.0 to 100	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT