

Sinvicomp SGH4340D

Flexible Polyvinyl Chloride

Teknor Apex Asia Pacific PTE. LTD.

Message:

SINVICOMP SGH4340D is a flexible polyvinyl chloride material. This product is available in the Asia-Pacific region and is processed by extrusion. The main characteristics of SINVICOMP SGH4340D are: high rigidity.
The typical application field of SINVICOMP SGH4340D is: hose

General Information			
Features	Rigidity, high		
Uses	Garden hose		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.41	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	87		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	17.7	MPa	ASTM D638
Tensile Elongation (Break)	200	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Thermal stability-Congo Red (190°C)	> 30	min	BS 2782
Additional Information			
Typical temperature profile for SINVICOMP compound is from 160°C to 185°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP. Feeding zone: 160°C Mixing zone: 160°C~170°C Metering zone: 170°C~180°C Nozzle/Die Zone: 185°C			
NOTE			

1. Clear compound

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT