

IROGRAN® A 92 P 4637

Thermoplastic Polyurethane Elastomer (Polyether)

Huntsman Corporation

Message:

IROGRAN A 92 P 4637 is a thermoplastic polyether-polyurethane for injection moulding and extrusion applications. Additional characteristics of the product are excellent microbial resistance, high low-temperature flexibility, especially suitable for cable jacket.

PERFORMANCE FEATURES

- Excellent hydrolysis resistance
- High microbial resistance
- High stability of melt
- Easy coloring
- Low-temperature flexibility

APPLICATIONS

For the production of jacket material for cables, jackets for high pressure hoses, spiral hoses, profiles.

General Information			
Features	Bacteria Resistant		
	Good Colorability		
	High Melt Stability		
	Hydrolysis Resistant		
	Low Temperature Flexibility		
	Microbe Resistant		
Uses	Cable Jacketing		
	Hose		
	Profiles		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.13	g/cm ³	
Melt Volume-Flow Rate (MVR) (190°C/21.6 kg)	55.0	cm ³ /10min	
Molding Shrinkage			
Flow	0.40	%	ASTM D955
--	0.90	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240, ISO 868
Shore A, Injection Molded	92		
Shore D, Injection Molded	39		

Mechanical	Nominal Value	Unit	Test Method
Abrasion ²	30	mm ³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ³			
100% Strain	8.96	MPa	ASTM D412
100% Strain	9.10	MPa	DIN 53504
300% Strain	14.1	MPa	ASTM D412
300% Strain	15.9	MPa	DIN 53504
Tensile Strength ⁴			
Break	33.6	MPa	ASTM D412
Break	45.0	MPa	DIN 53504
Tensile Elongation ⁵			
Break	670	%	ASTM D412
Break	600	%	DIN 53504
Tear Strength ⁶			
--	116	kN/m	ASTM D624
--	74	kN/m	ISO 34-1
Compression Set ⁷			ASTM D395, ISO 815
23°C, 24 hr	25	%	
70°C, 24 hr	41	%	
Bayshore Resilience	34	%	
Injection	Nominal Value	Unit	
Drying Temperature			
--	100 to 110	°C	
Hot Air Dryer	80.0 to 90.0	°C	
Drying Time			
--	3.0	hr	
Hot Air Dryer	3.0	hr	
Dew Point	-30.0	°C	
Rear Temperature	175 to 195	°C	
Middle Temperature	175 to 195	°C	
Front Temperature	175 to 195	°C	
Nozzle Temperature	180 to 200	°C	
Processing (Melt) Temp	170 to 195	°C	
Mold Temperature	20.0 to 70.0	°C	
Extrusion	Nominal Value	Unit	
Drying Temperature	100 to 110	°C	
Drying Time	3.0	hr	
Hopper Temperature	25.0 to 40.0	°C	
Cylinder Zone 1 Temp.	165 to 190	°C	
Cylinder Zone 2 Temp.	165 to 190	°C	
Cylinder Zone 3 Temp.	165 to 190	°C	

Cylinder Zone 4 Temp.	165 to 190	°C
Cylinder Zone 5 Temp.	165 to 190	°C
Adapter Temperature	175 to 195	°C
Die Temperature	175 to 200	°C

NOTE		
1.	Injection Molded	
2.	Injection Molded	
3.	Injection Molded	
4.	Injection Molded	
5.	Injection Molded	
6.	Injection Molded	
7.	Injection Molded	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT