

TEKAMID™ TB110M40

Polyamide 6

Mando Advanced Materials Co., Ltd.

Message:

TEKAMID™ TB110M40 is a Polyamide 6 (Nylon 6) product filled with 40% mineral. It is available in Asia Pacific. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Mineral,40% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm³	ASTM D792
Molding Shrinkage ¹			ASTM D955
Flow	0.80	%	
Across Flow	1.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	83.4	MPa	ASTM D638
Tensile Elongation (Break)	9.0	%	ASTM D638
Flexural Modulus	5200	MPa	ASTM D790
Flexural Strength	137	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	200	°C	
1.8 MPa, Unannealed	105	°C	
Peak Melting Temperature	220	°C	ASTM D2133
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	80.0 to 90.0	°C	
NOTE			

1. 60°C Mold Temperature

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

