

Styrolution PS 1200/1201

General Purpose Polystyrene
INEOS Styrolution Group GmbH

Message:

Styrolution PS 1200/1201 is a General Purpose Polystyrene product. It can be processed by extrusion or thermoforming and is available in Latin America or North America. Applications of Styrolution PS 1200/1201 include film, medical/healthcare, packaging and sheet.

Characteristics include:

Flame Rated

High Stiffness

General Information			
UL YellowCard	E57787-100082695	E57787-246266	E57787-246267
Features	General Purpose		
	Good Melt Strength		
	High Stiffness		
Uses	Bi-axially Oriented Film		
	Food Packaging		
	Sheet		
Agency Ratings	USP Class VI		
UL File Number	E57787		
Forms	Pellets		
Processing Method	Extrusion		
	Thermoforming		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Apparent Density			
-- ¹	0.59 to 0.64	g/cm ³	
-- ²	0.62 to 0.67	g/cm ³	
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.6	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	78		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3170	MPa	ASTM D638
Tensile Strength (Yield, 23°C)	52.4	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	3310	MPa	ASTM D790
Flexural Strength	107	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	21	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	95.0	°C	
Vicat Softening Temperature	109	°C	ASTM D1525 ³
CLTE - Flow	7.2E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (3.18 mm)	20	kV/mm	ASTM D149
Dielectric Constant (1.00 mm, 1 MHz)	2.50		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index ⁴	1.590		ASTM D542
Transmittance (550 nm)	88.0 to 90.0	%	ASTM D1003
Optical Density - 400-700 nm avg.	0.0460		
Extrusion	Nominal Value	Unit	
Melt Temperature	182 to 277	°C	
NOTE			
1.	without external lubricant		
2.	with external lubricant		
3.	Rate B (120°C/h), Loading 1 (10 N)		
4.	Sodium D line		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT