

LNP™ STAT-KON™ DD0001 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP STAT-KON* DD0001 is a compound based on Polycarbonate resin containing Carbon Powder. Added features of this material include: Electrically Conductive, Flame Retardant.
Also known as: LNP* STAT-KON* Compound D-FR ECO
Product reorder name: DD0001

General Information			
UL YellowCard	E121562-101345285		
Filler / Reinforcement	Carbon Powder		
Features	Electrically Conductive		
	Flame Retardant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage			
Flow : 24 hr	0.40	%	ASTM D955
Across Flow : 24 hr	0.40	%	ASTM D955, ISO 294-4
Flow : 24 hr	0.39	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.11	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.14	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3450	MPa	ASTM D638
--	3750	MPa	ISO 527-2/1
Tensile Strength			
Break	64.3	MPa	ASTM D638
Break	64.6	MPa	ISO 527-2
Tensile Elongation			
Break	3.7	%	ASTM D638
Break	3.2	%	ISO 527-2
Flexural Modulus	3520	MPa	ASTM D790, ISO 178
Flexural Strength			
--	117	MPa	ASTM D790
--	103	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			

23°C	23	J/m	ASTM D256
23°C ²	2.4	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	550	J/m	ASTM D4812
23°C ³	37	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	1.93	J	ASTM D3763
--	0.700	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	86.7	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	88.4	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	82.2	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	82.0	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	5.2E-5	cm/cm/°C	
Transverse : -40 to 40°C	5.2E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.70 mm, Testing by SABIC)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	249 to 260	°C	
Middle Temperature	254 to 266	°C	
Front Temperature	260 to 271	°C	
Processing (Melt) Temp	254 to 288	°C	
Mold Temperature	37.8 to 65.6	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

