

# HIPOLEN P® FY 6

Polypropylene Homopolymer

HIPOL A.D.

## Message:

Hipolen® P FY 6 is a homopolymer, suitable for fibers products.

Typical applications of Hipolen® P FY 6 are, flat Yarn for carpet backing , monofilaments, and geotextiles.

Hipolen® P FY 6 has a wide range of approval for contact with food but for specific applications, reference should be made to Hipol chemical industry.

General Information			
Features	High tensile strength		
	Homopolymer		
	Workability, good		
	Compliance of Food Exposure		
Uses	Monochrome high toughness line		
	monofilament		
	Textile applications		
	Fiber		
	Heavy packing bag		
Forms	Particle		
Processing Method	Film extrusion		
	Blow molding		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.3	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.0	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	9.0	%	ASTM D638
Fracture	800	%	ASTM D638
Flexural Modulus	1300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	95.0	°C	ISO 75-2/B
Vicat Softening Temperature	150	°C	ISO 306/A50
Extrusion	Nominal Value	Unit	

Melt Temperature	230 - 270	°C
Extrusion instructions		

Melt temperature, tubular film: 210 to 250°CStretch oven temperature: 150 to 160°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

