

VALOX™ 420SE0 resin

Polybutylene Terephthalate

SABIC Innovative Plastics

Message:

30% glass reinforced, UL94 V-0/5V rated. Numerous applications: edge trimmers, food mixer motor stator and commutator, cooling fan, connectors, bobbins, switches etc

General Information			
UL YellowCard	E45587-101092091	E207780-101092084	E207780-101513785
	E45587-101513788		
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Uses	Switch		
	Connector		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.63	g/cm ³	ASTM D792, ISO 1183
Specific Volume	0.610	cm ³ /g	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	42	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	29.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow ¹	0.10 - 0.50	%	Internal method
Flow: 3.20mm	0.50 - 0.70	%	Internal method
Transverse flow ²	0.40 - 0.80	%	Internal method
Transverse flow: 3.20mm	0.50 - 1.0	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.090	%	ISO 62
Equilibrium, 23°C, 50% RH	0.070	%	ISO 62
Outdoor Suitability	f2		UL 746C
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class r	119		ASTM D785
R scale	119		ISO 2039-2
Ball Indentation Hardness (H 358/30)	118	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ³	12000	MPa	ASTM D638
--	10000	MPa	ISO 527-2/1
Tensile Strength			
Yield ⁴	120	MPa	ASTM D638

Yield	120	MPa	ISO 527-2/5
Fracture ⁵	120	MPa	ASTM D638
Fracture	120	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁶	2.0	%	ASTM D638
Yield	1.9	%	ISO 527-2/5
Fracture ⁷	2.0	%	ASTM D638
Fracture	1.9	%	ISO 527-2/5
Flexural Modulus			
50.0mm span ⁸	9800	MPa	ASTM D790
-- ⁹	9500	MPa	ISO 178
Flexural Stress			
--	180	MPa	ISO 178
Fracture, 50.0mm span ¹⁰	186	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	22.0	mg	Internal method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹¹			ISO 179/1eA
-30°C	6.0	kJ/m ²	ISO 179/1eA
23°C	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹²			ISO 179/1eU
-30°C	50	kJ/m ²	ISO 179/1eU
23°C	50	kJ/m ²	ISO 179/1eU
Notched Izod Impact			
-30°C	57	J/m	ASTM D256
23°C	60	J/m	ASTM D256
-30°C ¹³	6.0	kJ/m ²	ISO 180/1A
23°C ¹⁴	7.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	620	J/m	ASTM D4812
-30°C ¹⁵	45	kJ/m ²	ISO 180/1U
23°C ¹⁶	45	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	5.00	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	212	°C	ASTM D648
0.45 MPa, unannealed, 100 mm span ¹⁷	220	°C	ISO 75-2/Be
1.8 MPa, unannealed, 3.20mm	200	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ¹⁸	195	°C	ISO 75-2/Ae
1.8 MPa, unannealed, 64.0mm span ¹⁹	200	°C	ISO 75-2/Af
Vicat Softening Temperature			

--	200	°C	ASTM D1525, ISO 306/B50, ISO 306/B120 ²⁰
--	220	°C	ISO 306/A50
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 40°C	2.5E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flow: 23 to 80°C	2.5E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	8.9E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: 23 to 80°C	1.2E-4	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.25	W/m/K	ISO 8302
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257, IEC 60093
Dielectric Strength			
1.60 mm, in Oil	24	kV/mm	ASTM D149
3.20 mm, in Air	19	kV/mm	ASTM D149
0.800mm, in oil	23	kV/mm	IEC 60243-1
1.60mm, in oil	22	kV/mm	IEC 60243-1
3.20mm, in oil	16	kV/mm	IEC 60243-1
Dielectric Constant			
100 Hz	3.80		ASTM D150, IEC 60250
1 MHz	3.70		ASTM D150
50 Hz	3.30		IEC 60250
60 Hz	3.30		IEC 60250
1 MHz	3.30		IEC 60250
Dissipation Factor			
100 Hz	2.0E-3		ASTM D150, IEC 60250
1 MHz	0.020		ASTM D150
50 Hz	1.0E-3		IEC 60250
60 Hz	1.0E-3		IEC 60250
1 MHz	0.010		IEC 60250
Arc Resistance ²¹	PLC 6		ASTM D495
Comparative Tracking Index (CTI)	PLC 3		UL 746
Comparative Tracking Index			IEC 60112
--	175	V	IEC 60112
Solution B	125	V	IEC 60112
High Amp Arc Ignition (HAI)	PLC 0		UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 4		UL 746
Hot-wire Ignition (HWI)	PLC 2		UL 746

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.400 mm	V-2		UL 94
0.710 mm	V-0		UL 94
2.00 mm	5VA		UL 94
Glow Wire Flammability Index (1.00 mm)	960	°C	IEC 60695-2-12
Oxygen Index	32	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	12	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 80	%	
Rear Temperature	243 - 266	°C	
Middle Temperature	249 - 271	°C	
Front Temperature	254 - 277	°C	
Nozzle Temperature	249 - 271	°C	
Processing (Melt) Temp	254 - 277	°C	
Mold Temperature	65.6 - 87.8	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	50 - 80	rpm	
Vent Depth	0.025 - 0.038	mm	
NOTE			
1.	Tensile Bar		
2.	Tensile Bar		
3.	5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	Type 1, 5.0 mm/min		
6.	Type 1, 5.0 mm/min		
7.	Type 1, 5.0 mm/min		
8.	1.3 mm/min		
9.	2.0 mm/min		
10.	1.3 mm/min		
11.	80*10*4 sp=62mm		
12.	80*10*4 sp=62mm		
13.	80*10*4		
14.	80*10*4		
15.	80*10*4		
16.	80*10*4		
17.	120*10*4 mm		
18.	120*10*4 mm		
19.	80*10*4 mm		

20.	标准 B (120°C/h), 载荷2 (50N)
21.	Tungsten electrode

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

