

Quadrant EPP ERTALON® 66 SA-C

Polyamide 66

Quadrant Engineering Plastic Products

Message:

Quadrant EPP ERTALON® 66 SA-C is a Polyamide 66 (Nylon 66) product. It is available in Europe. Typical application: Engineering/Industrial Parts.
Characteristics include:
Flame Rated
Creep Resistant
Good Stiffness
Heat Resistant
High Strength

General Information				
Features		Good Creep Resistance		
		Good Stiffness		
		Good Wear Resistance		
		High Heat Resistance		
		High Strength		
Uses		Machine/Mechanical Parts		
Appearance		Natural Color		
Forms		Preformed Parts		
		Rod		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
23°C, 24 hr, 3.00 mm	0.97	--	%	
Saturation, 23°C	8.5	--	%	
Equilibrium, 23°C, 50% RH	2.5	--	%	
Water Absorption				ISO 62
23°C, 3.00 mm ¹	1.8	--	%	
23°C, 3.00 mm ²	120.0	--	mg	
23°C, 3.00 mm ³	65.0	--	mg	
Service Temperature - Minimum	-30	--	°C	
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (M-Scale, 10.0 mm)	87	--		ISO 2039-2
Ball Indentation Hardness (10.0 mm)	155	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method

Tensile Modulus	3300	1450	MPa	ISO 527-2/1B/1
Tensile Stress (Yield)	86.0	50.0	MPa	ISO 527-2/1B/20
Tensile Strain (Break)	> 50	> 100	%	ISO 527-2/1B/20
Tensile Creep Modulus (1000 hr)	19.0	7.50	MPa	ISO 899-1
Compressive Stress				ISO 604/1
5% Strain	88.0	--	MPa	
2% Strain	47.0	--	MPa	
1% Strain	24.0	--	MPa	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	5.0	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break	--		ISO 179/1eU
Notched Izod Impact Strength	5.0	13	kJ/m ²	ISO 180/2A
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	75.0	--	°C	ISO 75-2/A
Continuous Use Temperature				
-- ⁴	75.0	--	°C	
-- ⁵	90.0	--	°C	
-- ⁶	170	--	°C	
Melting Temperature (DSC)	240	--	°C	
CLTE - Flow				
23 to 60°C	8.5E-5	--	cm/cm/°C	
23 to 100°C	1.0E-4	--	cm/cm/°C	
Thermal Conductivity (23°C)	0.28	--	W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+13	> 1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+14	> 1.0E+12	ohms·cm	IEC 60093
Electric Strength (1.00 mm, in Oil)	26	17	kV/mm	IEC 60243-1
Relative Permittivity				IEC 60250
100 Hz	3.80	7.40		
1 MHz	3.30	3.80		
Dissipation Factor				IEC 60250
100 Hz	0.013	0.13		
1 MHz	0.020	0.060		
Comparative Tracking Index	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Flame Rating			UL 94	
3.00 mm	HB	--		
6.00 mm	HB	--		
Oxygen Index	24	--	%	ISO 4589-2
NOTE				
1.	96 hrs			
2.	Weight, 96 hrs			
3.	Weight, 24 hrs			
4.	20000 hrs			
5.	5000 hrs			
6.	Short periods			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT