

DuraGrip® DGR 6240CL

Thermoplastic Elastomer

Advanced Polymer Alloys

Message:

DuraGrip® 6240CL is a Thermoplastic Elastomer (TPE) designed for injection molding and extrusion processes. DuraGrip® 6240CL has excellent clarity, soft-touch feel, a high coefficient of friction, and bonds well to polypropylene. DuraGrip® 6240CL is also FDA compliant pursuant to 21 C.F.R. 177.2600. DuraGrip® 6240CL is not hygroscopic and under normal conditions does not require drying.

General Information			
Features	High Friction		
	Good adhesion		
	Definition, high		
Agency Ratings	EU 2002/96/EC (WEEE)		
	FDA 21 CFR 177.2600		
RoHS Compliance	RoHS compliance		
Appearance	Clear/transparent		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.883	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	32	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	39		ASTM D2240, ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412, ISO 37
100% strain	1.14	MPa	ASTM D412, ISO 37
300% strain	1.78	MPa	ASTM D412, ISO 37
Tensile Strength (Yield)	6.94	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	760	%	ASTM D412, ISO 37
Tear Strength ¹	18.4	kN/m	ASTM D624
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (190°C, 200 sec ⁻¹)	155	Pa · s	ASTM D3835
Additional Information			
The value listed as Density -Specific Gravity, ASTM D792, was tested in accordance with ASTM D471.The value listed as Density, ISO 1183, was tested in accordance with ISO 2781.			
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

