

Sarlink® TPV 4775B40

Thermoplastic Vulcanizate

Teknor Apex Company

Message:

A highly engineered Thermoplastic Elastomer for use in demanding applications. Sarlink® X4775BLK40 is a black, low hardness UV stable grade possessing superior compression set, chemical resistance and high temperature performance. This product is a high flow material designed for injection molding applications that require superior flow properties.

General Information			
Additive	UV Stabilizer		
Features	Good Chemical Resistance		
	High Flow		
	High Heat Resistance		
	Low Compression Set		
	Low Hardness		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	0.908	g/cm ³	ASTM D792
--	0.910	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240, ISO 868
Shore A, 5 sec, Extruded	74		
Shore A, 5 sec, Injection Molded	76		
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412, ISO 37
Across Flow : 100% Strain	3.10	MPa	
Flow : 100% Strain	3.50	MPa	
Tensile Strength			ASTM D412, ISO 37
Across Flow : Break	6.60	MPa	
Flow : Break	6.00	MPa	
Tensile Elongation			ASTM D412, ISO 37
Across Flow : Break	490	%	
Flow : Break	410	%	
Tear Strength - Across Flow			
--	33.3	kN/m	ASTM D624
-- ¹	33	kN/m	ISO 34-1
Compression Set			ASTM D395, ISO 815

23°C, 22 hr	24	%	
70°C, 22 hr	36	%	
125°C, 70 hr	52	%	
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			
135°C, 1000 hr	-12	%	ASTM D573, ISO 188
100% Strain, 135°C, 1000 hr	5.0	%	ASTM D573
150°C, 168 hr	-22	%	ASTM D573, ISO 188
100% Strain, 150°C, 168 hr	2.0	%	ASTM D573
100% Strain 135°C, 1000 hr	5.0	%	ISO 188
100% Strain 150°C, 168 hr	2.0	%	ISO 188
Change in Ultimate Elongation in Air - Across Flow			
			ASTM D573, ISO 188
135°C, 1000 hr	-16	%	
150°C, 168 hr	-29	%	
Change in Durometer Hardness in Air			
			ASTM D573, ISO 188
Shore A, 135°C, 1000 hr	3.0		
Shore A, 150°C, 168 hr	1.0		
Change in Volume (125°C, 70 hr, in IRM 903 Oil)			
	74	%	ASTM D471, ISO 1817
Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary @ 206/s			
200°C	220	Pa · s	ISO 11443
200°C	220	Pa · s	ASTM D3835
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	3.0	hr	
Rear Temperature	177 to 216	°C	
Middle Temperature	177 to 216	°C	
Front Temperature	177 to 216	°C	
Nozzle Temperature	188 to 221	°C	
Processing (Melt) Temp	182 to 221	°C	
Mold Temperature	10.0 to 65.6	°C	
Back Pressure	0.0689 to 1.03	MPa	
Screw Speed	100 to 200	rpm	
Screw L/D Ratio	20.0:1.0		
NOTE			
1.	Method Ba, Angle (Unnicked)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT