

Isocor™ 6100

Polyamide 610

Shakespeare Monofilaments and Specialty Polymers

Message:

Isocor™ 6100 is a medium viscosity PA-610. This resin is specifically suited for applications requiring low moisture absorption and greater dimensional stability. Isocor™ 6100 is also used in applications requiring good electrical insulation properties. This resin can be processed using conventional techniques.

Typical applications for 6100 include:

cable jacketing

film extrusions

monofilaments / bristles

automotive tubing

electrical connectors

General Information	
Features	Good dimensional stability
	Low hygroscopicity
	Insulation
	General
	Medium viscosity
Uses	Films
	monofilament
	Cable sheath
	Pipe fittings
	Insulating material
	Connector
	Application in Automobile Field
Forms	Particle
Processing Method	Film extrusion
	Injection molding

Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.07	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.1	--	%	ASTM D955
Water Absorption (24 hr)	--	1.4	%	ASTM D570
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	60.0	51.7	MPa	ASTM D638
Tensile Elongation (Break)	100	300	%	ASTM D638
Flexural Modulus	2000	1300	MPa	ASTM D790

Taber Abrasion Resistance (1000 Cycles)	6.00	--	mg	ASTM D1044
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact	48	200	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	175	160	°C	ASTM D648
1.8 MPa, not annealed	66.1	60.0	°C	ASTM D648
Melting Temperature	215	--	°C	DSC
Injection	Dry	Unit		
Dew Point	< -17.8		°C	
Suggested Max Moisture	0.20		%	
Hopper Temperature	79.4		°C	
Rear Temperature	221 - 243		°C	
Middle Temperature	227 - 260		°C	
Front Temperature	238 - 271		°C	
Nozzle Temperature	238 - 271		°C	
Processing (Melt) Temp	238 - 271		°C	
Mold Temperature	10.0 - 93.3		°C	
Injection Pressure	3.45 - 13.8		MPa	
Injection Rate	Fast			
Back Pressure	0.345		MPa	
Extrusion	Dry	Unit		
Suggested Max Moisture	0.10		%	
Hopper Temperature	79.4		°C	
Cylinder Zone 1 Temp.	254		°C	
Cylinder Zone 2 Temp.	266		°C	
Cylinder Zone 3 Temp.	271		°C	
Cylinder Zone 4 Temp.	271		°C	
Die Temperature	271		°C	
Extrusion instructions				
Flange: 500°F (260°C)Air Dew Point (max): 0°F (-18°C)Neck: 500°F (260°C)Head: 480°F (250°C)Pump: 480°F (250°C)L/D Ratio: 24 to 30:1Compression Ratio: 3.5:1Polymer @ Die: 430°F (220°C)Screw Pressure: 2000 psi				

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

