

DuraGrip® DGR 6260TR

Thermoplastic Elastomer

Advanced Polymer Alloys

Message:

DuraGrip® 6260TR is designed to be a general purpose Thermoplastic Elastomer (TPE) that is easy to use in injection molding and extrusion processes. DuraGrip® 6260TR has an excellent soft touch, dry rubbery feel, and is highly elastic. It will bond to polypropylene and polyethylene, and is FDA compliant. DuraGrip® 6260TR is not hygroscopic and under normal conditions does not require drying.

General Information	
Features	Good adhesion
	General
Agency Ratings	EU 2002/96/EC (WEEE)
	FDA not rated
RoHS Compliance	RoHS compliance
Appearance	Translucent
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.886	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/5.0 kg)	4.1	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 5 sec)	58		ASTM D2240, ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412, ISO 37
100% strain	2.36	MPa	ASTM D412, ISO 37
300% strain	3.27	MPa	ASTM D412, ISO 37
Tensile Strength (Yield)	6.67	MPa	ASTM D412, ISO 37
Tensile Elongation (Break)	640	%	ASTM D412, ISO 37
Tear Strength ¹	24.9	kN/m	ASTM D624
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (190°C, 294 sec ⁻¹)	251	Pa · s	ASTM D3835

Additional Information

The value listed as Density -Specific Gravity, ASTM D792, was tested in accordance with ASTM D471. The value listed as Density, ISO 1183, was tested in accordance with ISO 2781.

NOTE

1. C mould

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

