

PROTEQ™ C16UST2Z

Polypropylene Copolymer

Marplex Australia Pty. Ltd.

Message:

PROTEQ™ C16UST2Z is a polypropylene copolymer containing 10% mineral filler which has been highly impact modified, heat stabilised and UV stabilised. PROTEQ™ C16UST2Z has been designed to meet the stringent requirements of automotive interior & exterior trim durability specifications, combining easy processing with low temperature toughness, rigidity, heat resistance, reduced gloss and improved marr resistance.

General Information	
Filler / Reinforcement	Mineral,10% Filler by Weight
Additive	Heat Stabilizer
	Impact Modifier
	UV Stabilizer
Features	Copolymer
	Good Processability
	Good Stiffness
	Good UV Resistance
	Heat Stabilized
	Impact Modified
	Low Gloss
	Low Temperature Toughness
	Medium Heat Resistance
Uses	Automotive Applications
	Automotive Exterior Trim
	Automotive Interior Trim

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.980	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	63		
Shore D, 15 sec	55		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (3.20 mm)	16.0	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	230	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	1600	MPa	ASTM D790

Flexural Strength ⁴ (3.20 mm)	31.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	150	J/m	
23°C, 3.20 mm	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed, 3.20 mm	92.0	°C	
1.8 MPa, Unannealed, 3.20 mm	55.0	°C	
CLTE - Flow	7.8E-5	cm/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Glow Wire Ignition Temperature (1.60 mm)	550	°C	AS/NZS 60695
Injection	Nominal Value	Unit	
Drying Temperature	85.0 to 90.0	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	205 to 225	°C	
Middle Temperature	215 to 235	°C	
Front Temperature	225 to 245	°C	
Processing (Melt) Temp	220 to 270	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	60.0 to 140	MPa	
Injection Rate	Moderate		
Back Pressure	0.100 to 0.500	MPa	
Screw Speed	40 to 60	rpm	
Clamp Tonnage	3.0 to 6.0	kN/cm ²	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	10 mm/min		
4.	10 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT