TOTAL Polypropylene PPH 3620WZ

Polypropylene Homopolymer

TOTAL Refining & Chemicals

Message:

TOTAL Polypropylene 3620WZ is engineered with nucleation to provide fast cycle time and improve contact clarity in thin wall multi-cavity molds. TOTAL Polypropylene 3620WZ contains an antistat that will help protect molded parts from dust accumulation.

TOTAL Polypropylene 3620WZ has passed USP Class VI testing, an all ingredients meet the chemical registration requirements of TSCA (U.S.) and DSL (Canada). TOTAL Polypropylene 3620WZ complies with all applicable FDA regulations for food contact applications.

TOTAL Polypropylene 3620WZ is particularly well suited for caps, closures, medical syringes and thin wall containers.

General Information				
UL YellowCard	E66261-247989			
Additive	Antistatic			
	Nucleating Agent			
Features	Antistatic			
	Fast Molding Cycle			
	Nucleated			
Uses	Caps			
	Closures			
	Medical/Healthcare Applications			
	Thin-walled Parts			
Agency Ratings	EC 1907/2006 (REACH)			
	FDA Food Contact, Unspecified Rating			
	USP Class VI			
RoHS Compliance	RoHS Compliant			
Forms	Pellets			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.905	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (230°C/2.16	10	40 ·		
kg)	12	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Rockwell Hardness (R-Scale)	107		ASTM D785	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Modulus	1720	MPa	ASTM D638	
Tensile Strength (Yield)	37.2	MPa	ASTM D638	
Tensile Elongation (Yield)	12	%	ASTM D638	
Flexural Modulus	1590	MPa	ASTM D790	

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	27	J/m	ASTM D256A
Unnotched Izod Impact (23°C)	850	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45			
MPa, Unannealed)	127	°C	ASTM D648
Melting Temperature	166	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

