

Anjacom® R050/75S Natural

Polycarbonate + ABS
Almaak International GmbH

Message:

Anjacom® R050/75S Natural is a Polycarbonate + ABS (PC+ABS) material. It is available in Europe for injection molding. Primary attribute of Anjacom® R050/75S Natural: Flame Rated.

General Information			
Features	Good Flow		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.14	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	27.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.40 to 0.80	%	
Flow	0.40 to 0.80	%	
Water Absorption			ISO 62
23°C, 24 hr	0.60	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-2/1
Tensile Stress (Yield)	60.0	MPa	ISO 527-2/50
Tensile Strain (Break)	5.0	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	45	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	108	°C	ISO 75-2/A
Vicat Softening Temperature	128	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	95.0	°C	
Drying Time	2.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	240 to 290	°C	
Mold Temperature	70.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

