

ALTECH® PP-H A 4940/506 MR40

Polypropylene Homopolymer

ALBIS PLASTIC GmbH

Message:

ALTECH® PP-H A 4940/506 MR40 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 40% talc. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

REACH Compliant

RoHS Compliant

Homopolymer

Stabilized

General Information			
Filler / Reinforcement	Talc,40% Filler by Weight		
Additive	Processing Stabilizer		
Features	Homopolymer		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/21.6 kg)	11	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3700	MPa	ISO 527-2
Tensile Stress	30.0	MPa	ISO 527-2
Flexural Modulus	4000	MPa	ISO 178
Flexural Stress	55.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	19	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	91.0	°C	ISO 75-2/A
Vicat Softening Temperature	100	°C	ISO 306/B120
Injection	Nominal Value	Unit	
Drying Temperature			
Circulation Dryer	60.0 to 90.0	°C	
Desiccant Dryer	60.0 to 90.0	°C	
Drying Time			
Circulation Dryer	2.0 to 4.0	hr	
Desiccant Dryer	2.0 to 4.0	hr	
Processing (Melt) Temp	200 to 270	°C	
Mold Temperature	20.0 to 70.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

