

Durethan® DP 2131/20 H2.0 900051

Polyamide 6

LANXESS GmbH

Message:

PA 6, 20 % glass fibers, injection molding, heat-aging stabilized, improved surface finish, improved resistance to weathering

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 20% filler by weight		
Additive		heat stabilizer		
Features		Good weather resistance		
		Thermal Stability		
		Excellent appearance		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.28	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.54	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.19	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.35	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.12	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	7600	--	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	150	--	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	--	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	6400	--	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	200	--	MPa	ISO 178/A
23°C ⁶	225	--	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	4.5	--	%	ISO 178/A
ISO Shortname	ISO 1874 PA 6, GHR, 14-080, GF20			ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA

-30°C	< 10	--	kJ/m ²	ISO 179/1eA
23°C	< 10	--	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	40	40	kJ/m ²	ISO 179/1eU
23°C	45	60	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	< 10	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	35	--	kJ/m ²	ISO 180/1U
23°C	35	--	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	4.00	--	J	ISO 6603-2
23°C	5.00	--	J	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	213	--	°C	ISO 75-2/B
1.8 MPa, not annealed	215	--	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	--	°C	ISO 306/B120
Melting Temperature ⁸	222	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	2.3E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	8.9E-5	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	2.0E+15	2.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	3.0E+15	1.0E+12	ohms·cm	IEC 60093
Relative Permittivity				IEC 60250
23°C, 100 Hz	4.10	9.34		IEC 60250
23°C, 1 MHz	3.74	4.27		IEC 60250
Dissipation Factor				IEC 60250
23°C, 100 Hz	8.0E-3	0.22		IEC 60250
23°C, 1 MHz	0.018	0.065		IEC 60250
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94
Injection	Dry	Unit	Test Method	

Drying Temperature - Dry Air Dryer	80.0	°C
Drying Time - Dry Air Dryer	2.0 - 6.0	hr
Processing (Melt) Temp	270 - 290	°C
Mold Temperature	80.0 - 120	°C

NOTE

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

